



SSUK POLYSPORT RANGE DUPLIX VS 41 /43 P TIMBER SYSTEMS

Technical Data:		Polysport Duplex VS 41 P	Duplex VS 43 P
Layers	Thickness of system:	40.5mm	43mm
	Top layer:	Parquet 13,5 mm thick with a solid timber veneer approx. 3.5 mm supplied with a factory PU pre-finished coating, tongue and groove joints fixed with special nails	Parquet 16 mm thick with a solid timber veneer approx. 5.1 mm supplied with a factory PU pre-finished coating, tongue and groove joints fixed with special nails
	load distribution layer:	12 mm Multi-Function-Panel (MFP) to EN 13986 P5, with standard dimension 2,5 m x 1,25 m	12 mm Multi-Function-Panel (MFP) to EN 13986 P5, with standard dimension 2,5 m x 1,25 m
	elastic layer:	15 mm PUR composite foam	15 mm PUR composite foam
Test results according DIN 10832:	shock absorption:	60,0%	59,0%
	vertical deformation:	3,5 mm	3,2 mm
	rolling load without damage:	more than 1500 N without damage	more than 1500 N without damage
	ball rebound:	98,0%	99,0%
	dynamic friction:	0,40	0,40